

Product Description

Polyeuro® 5502 is a fast setting, rapid curing, 100% solids, flexible, aromatic, two component, spray polyurea that can be applied to suitably prepared concrete and metal surfaces. It has extremely fast gel time making it suitable for applications down to -20°F (-28.89°C). It may be applied in single or multiple applications without appreciable sagging and is relatively insensitive to moisture and temperature allowing application in most temperatures. Polyeuro® 5502 offers a tack free time of less than sixty seconds and exhibits 400% ± 50% elongation upon curing with 50 Shore D hardness.

Features

- Coats Carbon or Mild Steel Metals Without Primer
- Elastomeric
- Excellent Thermal Stability
- Good Chemical Resistance
- Installed With or Without Reinforcement in Transitional Areas
- Low Temperature Flexibility
- Meets USDA Criteria
- Odorless
- Seamless
- Zero VOC (100% Solids)

Typical Uses

- Cold-Storage Facilities
- Fertilizer Plants
- Food-Processing Plants
- Industrial and Manufacturing Facilities
- Landfill Containment
- Manholes
- Marine Environments
- Mining Operations
- Paper and Pulp Mills
- Parking Garage Decks
- Pen Stocks
- Power Plants
- Refineries
- Secondary Containment
- Structural Steel
- Walkways and Balconies
- Warehouse Floors

Packaging

10-gallon kit	5 gallons (18.9 liters) Side-A and 5 gallons (18.9 liters) Side-B
100-gallon kit	50 gallons (189 liters) Side-A and 50 gallons (189 liters) Side-B

Technical Data (Based on Draw Down Film)

Mix Ratio by Volume	1A : 1B
Pot Life @150-160°F (65.5-71°C), 50% R.H.	4-8 seconds
Tack Free Time (thickness & substrate temperature dependent)	45-60 seconds
Recoat Time	0-6 hours
Viscosity at 150-160°F (65.5-71°C)	
Side-A	100 ± 20 cps
Side-B	50 ± 20 cps
Density (Side-A & Side-B Combined)	8.81 lbs/gal
Flash Point	> 200°F (93.3°C)
Hardness, ASTM D2240	50 ± 5 Shore D
Tensile Strength, ASTM D412*	3000 ± 200 psi 20.68 ± 1.37 MPa
Elongation, ASTM D412*	400 ± 50%
Tear Resistance, ASTM D624*	450 ± 50 pli 78.8 ± 8.8 kNm
Service Temperature - Dry	-40°F to 250°F -40°C to 121°C
Service Temperature - Wet	40°F to 120°F 4.44°C to 48.89°C
Water Vapor Permeance (Procedure B) ASTM E96	0.88 perm-inch
Volatile Organic Compounds, (Side-A & B combined) ASTM D2369-81	0 lbs/gal 0 gm/liter
Minimum Applied Thickness	1 mm
Return to Service: Foot Traffic	1-4 hours
Return to Service: Full Service	> 24 hours
Taber Abrasion Resistance, ASTM D4060 (CS17 wheel, 1000 cycles, 1 kg load) (maximum)	6 mg loss
Hydrostatic Pressure Test, ASTM D5385-93106, Para 7.0	Pass Hold 100 psi
Crack Bridging, ASTM C1305 (10 cycles @ -15°F [-25.5°C], Rate 0.125 inch/hr, Ext. -0.125 inch)	Pass
Volume Resistivity, ASTM D257	6.0 x 10 ¹² ohm.cm
Water Absorption, ASTM D471 (maximum 74°F or 23°C, 24 hours)	< 2%
Impact Resistance @ 77°F or 25°C (ASTM G14)	> 150 in. lbs
Pull-Off Strength (minimum), ASTM D4541, Inter-Coat Adhesion (within recoat time)	Excellent
Concrete (Shot Blasted and Primed), substrate failure occurred	>500 psi (3.4MPa)
Steel (90 µm blast profile)	>900 psi (6.2 MPa)
Lineal Shrinkage	1 - 2%
Flexibility (1/8" 3mm Mendrel Bend Test), ASTM D1737	Pass
Resistance to Weathering, ASTM G-23 (Type QUV Weatherometer-3000 hrs exposure)	No cracking or blistering. Color change, gloss reduction & chalking are noted.
Fire Test, ASTM E108 (Non Combustible Surface)	Pass Class A

*These physical properties from sample sprayed with Graco EXP2 @ 2000 psi minimum, with Fusion Gun AR4242 @ 150-160°F (65°C to 71°C). Different machine and parameter will change these properties. User should perform their own independent testing as properties are approximate.

Colors

Clear/Neutral. Custom colors are available upon request. Color Packs, when used, must be added to Side-B.

Due to its aromatic composition, Polyeuro® 5502 will tend to yellow or darken in color and will become flat after exposure to UV light. A topcoat can be applied to Polyeuro® 5502 within six hours of application with an aliphatic polyurethane/polyurea coating for a colorfast finish.

Coverage

Polyeuro® 5502 may be applied at any rate to achieve desired thickness. Theoretical coverage for 1 mil (0.254 microns) thickness is one gallon per 1600 sqft (3.78 liters per 149 sqm).

Estimating Formula: (1600 sqft per gal /Dry Mil Thickness) x Solids Content = Application Rate per gallon.

Surface Preparation

In general, coating performance and adhesion are directly proportional to surface preparation. Most failures in the performance of surface coatings can be attributed to poor surface preparation. Polyurea coatings rely on the structural strength of the substrate to which they are applied. All surfaces must be free of dust, dirt, oil, grease, rust, corrosion and other contaminants. When coating previously used substrates, it is important to consider the possibility of substrate absorption, which may affect the adhesion of the coating system, regardless of the surface preparation. Polycoat recognizes the potential for unique substrates from one project to another. The following information is for general reference. For project-specific questions, contact Polycoat.

NEW AND OLD CONCRETE

Refer to SSPC-SP13/NACE 6, or ICRI 03732: CSP 3-5. New concrete must be cured for 28 days prior to product application. Surface must be clean, dry, sound and offer sufficient profile for product adhesion. Remove all dust, dirt, oil, form release agents, curing compounds, salts, efflorescence, laitance and other foreign matter by shotblasting and/or suitable chemical means, in accordance with local chemical regulations. Rinse thoroughly to achieve a pH between 8.0 and 11.0. Allow to dry completely. If old concrete has a surface that has deteriorated to an unacceptably rough surface, PC-260 or a mixture of Polyprime® 21 and sand should be used as a repair agent for cracks, spalls, bug holes and voids. Upon full cure of the repair agent, prime the entire surface intended for coating.

CONCRETE SURFACE PREPARATION REFERENCE

ASTM D4258 - Standard practice for cleaning concrete.
ASTM D4259 - Standard practice for abrading concrete.
ASTM D4260 - Standard practice for etching concrete.
ASTM F1869 - Standard test method for measuring moisture vapor emission rate of concrete.
ICRI 03732 - Concrete surface preparation.

WOOD

All wood should be clean, dry and free of any knots, splinters, oil, grease or other contaminants. Splintered or rough areas should be sanded. Knots should be repaired using PC-260 with sand. Upon full cure of the repair agent, prime the entire surface intended for coating.

STEEL (ATMOSPHERIC AND IMMERSION EXPOSURE)

Remove all oil, grease, weld spatters and round off any sharp edges from surface. Minimum surface preparation is Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Optimum surface profile is 2-3 mils. Prime and shoot Polyeuro® 5502 onto any bare metal the same day as it is cleaned to minimize any potential flash rusting.

ALUMINUM

Aluminum should be blasted with aluminum oxide or sand, and not with steel or metal grit. Excessive blasting may result in a warped or deformed surface. After blasting, wash aluminum with a commercially available aluminum cleaner. Allow to dry, then prime.

BRASS AND COPPER

Brass and copper should be blasted with sand, and not with steel or metal grit. Remove all dust and grease prior to applying primer.

GALVANIZED SURFACES

Clean and degrease any contaminated surfaces before priming. Do not blast galvanized surfaces with an abrasive grit. An adhesion test is recommended prior to starting the project.

FIBERGLASS REINFORCED PLASTIC

The gel coat should be lightly blasted or sanded with 80 grit sandpaper and cleaned.

PLASTIC FOAMS

Enhanced adhesion is obtained when the foam is mechanically abraded. When coating polystyrene, do not use a solvent-based primer.

TEXTILES, CANVAS, FABRICS

Adhesion to most fabrics, geothermal membranes and textiles does not require a primer.

STAINLESS STEEL

Stainless steel may be grit blasted and degreased before priming. Some stainless steel alloys are so inert that it is not possible to achieve a satisfactory bond. An adhesion test is recommended prior to starting the project.

NEW AND OLD CAST IRON

Blast with a steel grit and degrease before priming. Old cast iron is difficult to prepare for a satisfactory bond. It can absorb oil and water soluble contaminants that will keep returning to the surface after the coating system has been applied and affect the coating system adhesion. An adhesion test is recommended prior to starting the project.

ALL OTHER SURFACES

An adhesion test is recommended prior to starting the project.

Mixing

Polyeuro® 5502 may NOT be diluted under any circumstances. Thoroughly mix Polyeuro® 5502 Side-B with air driven power equipment until a homogeneous mixture and color is attained.

Application

Both Side-A and Side-B materials should be preconditioned to 75-80°F (24-27°C) before application.

Recommended surface temperature must be at least 5°F (3°C) above the dew point.

Polyeuro® 5502 should be applied using a plural component, heated, high pressure 1:1 spray mixing equipment like Graco's Reactor, Glass Craft or other equivalent machine may be used.

Both Side-A and Side-B materials should be sprayed at a minimum of 2000 psi and at temperatures above 150°F (66°C).

Adequate pressure and temperature should be maintained at all times. Polyeuro® 5502 should be sprayed in smooth, multidirectional passes to improve uniform thickness and appearance.



**POLYCOAT
PRODUCTS**

A Division of American Polymers Corp.

TECHNICAL DATA SHEET | Section 9.1

POLYEURO® 5502

Two Component, Aromatic, Polyurea Protective Coating

Storage

Polyeuro® 5502 has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Side-A and Side-B drums are recommended to be stored above 60°F (15°C). Avoid freezing temperatures.

Store drums on wooden pallets to avoid direct contact with the ground. If stored for a long period of time, rotate Side-A and Side-B drums regularly.

Limitations

Do not open until ready to use. Both Side-A and Side-B containers must be fitted with a desiccant device during use.

Warning

This product contains Isocyanates and Curative Material.

Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2020 Polycoat Products. All rights reserved. Revision 2020918.DM